

SAC0307-1101H

High temperature Lead-free Solder Bar

The SAC0307-1101H solder bar is primarily composed of high-purity tin, along with high-purity silver and copper. It has been refined using advanced professional equipment and exceptional technology to create an environmentally friendly, lead-free solder bar with outstanding welding performance.

FEATURES

- Less metal impurity and low oxide content and high purity.
- After molten tin liquid surface smooth, level off, low viscosity, excellent liquidity.
- Unique high oxidation performance of tin slag quantity is few.
- Good wettability, surface tension is small, easy to tin, bright spot, full, welding quality is stable and reliable.
- Green environmental protection products, in line with RoHS environmental protection requirements, etc.

APPLICATION

SAC0307-1101H High temperature lead-free solder bar is widely applied to communications equipment, instrumentation equipment, audio and video multimedia equipment, automotive industry, household electrical and electronic equipment and other electronic products of wave soldering reliability, precision welding and special welding technology, such as manual welding and automatic welding, such as spraying, electroplating.

TYPICAL PROPERTIES

Items	Technical Parameters	Standards
Part Number	SAC0307-1101H	/
Metal Alloy	Sn99.3/ Ag0.3 /Cu0.7	/
Appearance	Silvery White, Trapezoidal cross-section of strip casting alloys	Visual Inspection
Melting Point(°C)	217-227	GB/T 20422-2006
Density (g/cm ³)	7.3	GB/T 20422-2006
RoHS	PASS	RoHS
Shelf Life	2 years	From MGF
Packaging	20kg/box & 1kg/Roll	/

ALLOY COMPOSITION

No.	Items	CAS. No	Content (%)
Key Metal Alloy			
1	Tin (Sn)	7440-31-5	Surplus Quantity
2	Silver (Si)	7440-22-4	0.3±0.1
3	Copper (Cu)	7440-50-8	0.7±0.1
Impurity Limit			
4	Lead (Pb)	7439-92-1	≤0.10
5	Iron (Fe)	7439-89-6	≤0.02
6	Bismuth (Bi)	7440-69-9	≤0.10
7	Stibium (Sb)	7440-36-0	≤0.10
8	Indium (In)	7440-74-6	≤0.10
9	Zincum (Zn)	7440-66-6	≤0.001
10	Aurum (Au)	7440-57-5	≤0.05
11	Nickel (Ni)	7440-02-0	≤0.01
12	Aluminum (Al)	7429-90-5	≤0.001
13	Cadmium (Cd)	7440-43-9	≤0.002
14	Arsenic (As)	7440-38-2	≤0.03

DIRECTION OF USES

- After using for a period of time, the composition of alloys will be changed, and that will lead to decline the welding performance and mechanical properties of solder, so the composition of solder alloys should be adjusted regularly by using pure tin. (Advice: every 10-15 day per time)
- Soldering temperature is about 350--450. (Furnace inside practical testing temperature °C)

The data contained in this bulletin is provided only as a guide for evaluation/consideration. These material characteristics are typical properties that are based on a limited number of samples tested in the laboratory. We cannot assume responsibility for results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any product or method. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide.