

## UV3701

### Photo-light & UV Curing Adhesive

UV3701 is a one-component, UV-curable, acrylic adhesive. This product is specifically designed for electrical bonding, fixing, and covering protection of sub-components. The product features medium viscosity, fast curing speed, good weather resistance, and flame retardancy among other resistances.

### UNCURED PROPERTIES

Properties	Reference
Chemical composition	Polyurethane acrylic resin
Physical state	Liquid
Appearance	Milky white viscous liquid
Viscosity (25°C, spindle viscometer 4#12 mPa.s)	12000-18000
Specific gravity Kg/L	1.08
Solvent content (%)	0
Heavy metal content PPM	0

Properties	Test method	Reference
Hardness Shore D	GB/T 2411-2008	73-78
Operating temperature range	-40-130 °C	Customers conduct self-test with workpieces
Shear strength	PC/ABS	≥ 25N/cm <sup>2</sup>
Peel strength	PC/ABS	≥ 15N/cm <sup>2</sup>

### ELECTRICAL PROPERTIES

Properties	Test method	Reference
Dielectric constant (100MHz)	GB/T 1409-2006	3.08
Dielectric loss (1MHz)	GB/T 1409-2006	0.03
Dielectric strength (KV/mm)	GB/ 1048.1-2016	26.7
Surface resistivity (Ω)	GB/T 31838.3-2019	1.49x10 <sup>16</sup>
Volume resistivity (Ω.cm)	GB/T 31838.2-2019	4.64x10 <sup>14</sup>

### CURING PROPERTIES

Curing will occur under sufficient ultraviolet irradiation. The curing speed and depth depend on the light intensity, spectral distribution of the light source, irradiation time and the light transmittance of the adhered material. The following data are measured under the condition of ultraviolet radiation of 20mw/cm<sup>2</sup> produced by a high-pressure mercury lamp:

Properties	Reference
Tack free time (1mm)	5-10 s
Deep curing time (1mm)	15-20 s
Full cure energy (1mm)	600 mJ/cm <sup>2</sup>

\*Recommended Curing Equipment: CUV-1800M Mercury UV Curing System

### CURED PROPERTIES

The following data are measured after curing with a high-pressure mercury lamp source with a cumulative energy of 600mj/cm<sup>2</sup>

### STABILITY TEST

The following data are measured after curing with a high-pressure mercury lamp source with a cumulative energy of 600mj/cm<sup>2</sup>.

## UV3701

*Photo-light & UV Curing Adhesive*

Base material	Test conditions	Bonding strength rate (%)
PC/GLASS	65°C 90%RH (72H)	80
PVC/GLASS	65°C 90%RH (72H)	75
Stainless/PVC	65°C 90%RH (72H)	82
Stainless/GLASS	65°C 90%RH (72H)	92

### STORAGE

Please store in a cool and dark place. Please close the bottle cap after opening it. Do not pour the unused glue back into the original bottle. The optimal storage temperature is 8-28°C. Too high or too low will affect the performance of the glue. The shelf life is 8 months.

The data contained in this bulletin is provided only as a guide for evaluation/consideration. These material characteristics are typical properties that are based on a limited number of samples tested in the laboratory. We cannot assume responsibility for results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any product or method. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide.